## **PP-4130-MFill3**



# **Polypropylene Compound Reinforced with Glass Fiber**

## **Injection Grade**

## **Technical Data Sheet**

#### **Product Description**

**PP-4130-MFill3** is Co-polymer Polypropylene based Compound in natural color reinforced with <u>20%</u> of Chopped Glass Fiber. This grade has good mechanical properties, high impact resistance, good thermal properties and dimensional stability. It is designed for use in a wide range of injection parts especially in automotive industry.

#### General

Material Status: Available

Processing Method: injection molding

Form: Pellet Color: Natural

Properties	Nominal Value	Test Method
Density	1.05 g/cm³ (±0.01)	ASTM D792
MFI (230°C/ 2.16kg)	7 g/10 min (±1)	ASTM D1238
Izod Impact, Notched	15 kj/m²(±1)	l y 150 180 r s
Tensile Strength at Yield	60 MPa (±5)	ASTM D638
Elongation at Break	5% (±1)	ASTM D638
Elastic Modulus	3500 MPa (±200)	ASTM D638
Heat Deflection Temperature (0.45MPa)	150 °C (±5)	ASTM D648

Typical Properties: These values are not to be considered as product specifications

For more details please contact us

www.modiranpolymer.com