# **PP-2170-MFill3**



# **Polypropylene Compound Reinforced with Glass Fiber**

## **Injection Grade**

## **Technical Data Sheet**

#### **Product Description**

**PP-2170-MFill3** is Homo-polymer Polypropylene based Compound in natural color reinforced with 40% of Chopped Glass Fiber. This grade has good mechanical properties, impact resistance, thermal properties and dimensional stability. It is designed for use in a wide range of injection parts especially in automotive industry.

#### **General**

Material Status: Available

Processing Method: injection molding

Form: Pellet Color: Natural

Properties	Nominal Value	Test Method
Density	1.25 g/cm <sup>3</sup> (±0.01)	ASTM D792
MFI (230°C/ 2.16kg)	1 5 g/10 min (±1)	o I y astm d1238 x s
Izod Impact, Notched	9 kj/m² (±2)	ISO 180
Tensile Strength at Yield	80 MPa (±5)	ASTM D638
Elongation at Break	4% (±1)	ASTM D638
Elastic Modulus	6000 MPa (±200)	ASTM D638
Heat Deflection Temperature (0.45MPa)	165 °C (±5)	ASTM D648

Typical Properties: These values are not to be considered as product specifications

For more details please contact us

www.modiranpolymer.com