## **PP-2150-MFill3**

## **Polypropylene Compound Reinforced with Glass Fiber**



**Injection Grade** 

Technical Data Sheet

## **Product Description**

**PP-2150-MFill3** is Homo-polymer Polypropylene based Compound in natural color reinforced with <u>30%</u> of Chopped Glass Fiber. This grade has good mechanical properties, impact resistance, thermal properties and dimensional stability. It is designed for use in a wide range of injection parts especially in automotive industry.

General		
Material Status: Available Processing Method: injection molding Form: Pellet Color: Natural		
Properties	Nominal Value	Test Method
Density	1.12 g/cm <sup>3</sup> (±0.01)	ASTM D792
MFI (230°C/ 2.16kg)	5 g/10 min (±1)	ASTM D1238
Izod Impact, Notched	<b>r i</b> 9 kj/m <sup>2</sup> (±1) <b>P</b> o	l y 150 180 r s
Tensile Strength at Yield	75 MPa (±5)	ASTM D638
Elongation at Break	4% (±1)	ASTM D638
Elastic Modulus	4000 MPa (±200)	ASTM D638
Heat Deflection Temperature (0.45MPa)	165 °C (±5)	ASTM D648

Typical Properties: These values are not to be considered as product specifications

For more details please contact us

www.modiranpolymer.com